



11390, Armand-Chaput Montréal, QC, Canada H1C 1S7
 Tél. : (514) 643-0800 Fax : (514) 643-0959
 Internet : www.accocinema.com
 Licence # RBQ 2858-5883-23

TECHNICAL SHEET (Black fiberglass veil)

GENERAL DESCRIPTION :

Blen of polyester and glass fiber with a latex binder system including:

- Fire retardant chemistry
- An EPA registered biocide
- A high level of water holdout treatment

PRESENT USE: Flexible, non-wrinkling insulation facing

<u>PROPERTY</u>	<u>ENGLISH</u>	<u>METRIC</u>	<u>TEST METHOD BASED ON</u>
BASIS WEIGHT	33.5 (lb/2880 sq.ft.) 1.2 (lb/100 sq.ft.)	56.8 (g/m ²)	ASTM D-646
LOI	49.0 (%)	49.0 (%)	ASTM D-828
TENSILE			
Machine Direction	15.2 (lb/in)	6.8 (kg/25mm)	
Cross Direction	13.7 (lb/in)	6.1 (kg/25mm)	
TEAR RESISTANCE			
Cross Direction	1.2 (lb)	536 (g)	TM-018
MULLEN	45 (psi)	310 (kPa)	ASTM D-774
OPACITY	68.7 (%)	68.7 (%)	TM #042B
60 % IPA HOLDOUT	> 5 (min)	> 300 (sec)	IST 80.6-92
PERMEABILITY	500 (ft ³ /min/ft ²)	250 (cm ³ /s/cm ²)	ASTM D-737